

WOOD

BÄCKASKOG BRANTEVIK

PRODUCT DATASHEET 2018



TECHNICAL DATA (EN 13489)		
Reaction to fire	EN 14342 Table 1 (when applicable) / EN 13501	Dfl-s1
Emission of formaldehyde	EN 14342	E1
Brinell hardness (average value) Oak	(BHN) EN1534	3,7
Taber Abraser/Lacquer's wear resistance Protoco Natura <i>These typical values are not applicable for stained, brushed or hardwax oiled products.</i>	EN 13696	3500
Reduction of sound weighted index ΔL_w in dB with 2 mm Tarkofoam/flex II	NF EN ISO 140-8 / Acc to NF EN ISO 717-2	17
Thermal insulation value (RT m ² K/W) board only with rag felt with 2 mm Tarkofoam/flex II	EN ISO 10456:2007	0,101 0,121 0,141
Thermal conductivity (W/m K) 13 mm	EN 12664 / EN 14342:2013	0,104

INSTALLATION	
Installation method	2-lock for floating or glue down
Installation instruction	Download from www.tarkett.com Contact your supplier for more details
Underfloor heating compatible Maximum floor surface temperature 27°C with self-regulating under-floor heat system	Yes
Start & Stop: Shorter lengths of planks included in approx. 1 pack per 20 m ²	

DIMENSIONS & PACKAGE	13x194x2281
Thickness EN 13489 (mm)	13
Width (mm)	194
Length (mm)	2281
Wear layer thickness (mm)	2,5
Boards/pack	6
m ² /pack	2,66
m ² /pallet	106,4
Net weight/m ² (kg)	7,3

RECOMMENDED ACCESSORIES	
Installation	Tarkofoam II / Tarkoflex II Installation kit
Aesthetics	Skirting Transition moulding Pipe covers
Care & Maintenance	Wood Floor Care Kit / Spray Mop Kit Bioclean Refresher
See more alternatives and the complete range of accessories @ www.tarkett.com	

Hanaskog 2018.09

PRODUCT DATA	Material code	Dimensions (mm)			Pattern	Surface treatment	Surface effect	Bevel (2 side)	Stained	DoP no.
		Thickness	Width	Length						
Oak White Brantevik	8723029	13	194	2 281	3-strip	Protoco Natura	-	-	Yes	0020-0104
Oak Bäckaskog	8723022	13	194	2 281	3-strip	Protoco Natura	-	-	No	0020-0104

Brantevik/Bäckaskog 13 mm

98 % 98 % Natural Renewable	100 % Recyclable
--------------------------------------	---------------------

